

**TEST REPORT OF 30 MICRON MULCHING FILM AS PER IS 2508**

SL No	PARTICULARS	READING	Description
1	AVERAGE GSM	26.9	
2	DART IMPACT	75 GM	FROM 66CM HEIGHT
	MICRON	29-31	
3	TENSILE STRENGTH BRAKES		
	(A)Machine Direction	133.33	KG/SQCM
	(B)Transverse Direction	121.11	KG/SQCM
4	ELOGATION AT BREAK		
	(A) Machion Direction	480%	
	(B) Transverse Direction	520%	
5)	Opaque	100%	

**DETAILS**

- 1) 3 LAYER
- 2) 6% UV In Each Layer (Ampasit Company)
- 3)2% Anti -Oxidant in each layer
- 4)2% Anti sulphur in each layer
- 5)Bottom layer master batch black 8%
- 6)Middle layer white 8% master batch
- 7)Top layer silver 8% master batch

We certified that above details are provided by in house lab test report with all the standard norms and procedures.

**AN ISO 9001:2015 UQ 1051018011 CERTIFIED COMPANY**

| Mulching Film | Tarpaulin | Pond Lining | Nursery Bags | Shade Net |

Plot #15, Agro Division APMC Yard, Behind Exhibition & Govt. Printing Press, Amargol-Hubballi - 580 025

Karnataka (INDIA) T:0836-2363955 M:94490 63955 E: sales.plastic@alagundagigroups.com